

# CARATTERISTICHE TECNICHE















Gres porcellanato smaltato impasto colorato

# TECHNICAL FEATURES

Glazed through body porcelain stoneware

# TECHNISCHE EIGENSCHAFTEN\*

Glasiertes Durchgefärbtes Feinsteinzeug\*

	NORME TEST N°	DESCRIZIONE DESCRIPTION	VALORE A NORMA REQUIRED STANDARD	VALORE - MATT RESULTS - MATT	VALORE - LEV. RESULTS - LEV.
	ISO 10545/3	ASSORBIMENTO D'ACQUA WATER ABSORPTION ABSORPTION D'EAU WASSERAUFNAHME	≤ 0,5%	CONFORME	CONFORME
	ISO 10545/4	RESISTENZA ALLA FLESSIONE BENDING STRENGTH RESISTANCE A LA FLEXION BIEGFESTIGKEIT	R ≥ 35 N/mm <sup>2</sup>	CONFORME	CONFORME
	ISO 10545/8	COEFFICIENTE DI DILATAZIONE TERMICA LINEARE THERMAL EXPANSION COEFF. BETWEEN 20°C - 100°C COEFF. DE DILATATION THERMIQUE LINEAIRE ENTRE 20°C ET 100°C WÄRMEAUSSDEHNUNG ZWISCHEN 20°C UND 100°C	≤ 9x10 <sup>-6</sup>	9x10 <sup>-6</sup> °C <sup>-1</sup>	9x10 <sup>-6</sup> °C <sup>-1</sup>
	ISO 10545/9	RESISTENZA AGLI SBALZI TERMICI RESISTANCE TO THERMAL SHOCK RESISTANCE AUX CHOCX THERMIQUES TEMPERATURWECHSELBESTÄNDIGKEIT		RESISTE RESISTANT RÉSISTE BESTÄNDIG	RESISTE RESISTANT RÉSISTE BESTÄNDIG
	ISO 10545/11	RESISTENZA AL CAVILLO CRAZING RESISTANCE RESISTANCE AU TRASSAILAGE HAARRISSFESTIGKEIT		RESISTE RESISTANT RÉSISTE BESTÄNDIG	RESISTE RESISTANT RÉSISTE BESTÄNDIG
	ISO 10545/14	RESISTENZA ALLE MACCHIE STAIN RESISTANCE RESISTANCE AUX TACHES FLECKENFESTIGKEIT	min. Classe 3	CONFORME	CONFORME
	ISO 10545/13	RESISTENZA ALL'ATTACCO CHIMICO CHEMICAL RESISTANCE RESISTANCE A L'ATTAQUE CHIMIQUE FÄHIG GEGEN SÄUREN UND LAUGEN	min. GB	CONFORME	CONFORME
	ISO 10545/2	LUNGHEZZA E LARGHEZZA LENGTH AND WIDTH LONGUEURE ET LARGEUR LÄNGE UND BREITE	± 0,5%	CONFORME	CONFORME
	ISO 10545/2	SPESSORE THICKNESS EPAISSEUR STÄRKE	± 5%	CONFORME	CONFORME
	ISO 10545/2	ORTOGONALITÀ WEDGING ORTHOGONALITÉ RECHTWINKLICHKEIT	± 0,6%	CONFORME	CONFORME
	ISO 10545/2	PLANARITÀ WARPAGE PLANÉITÉ EBENFLÄCHIGKEIT	± 0,5%	CONFORME	CONFORME
	ISO 10545/12	RESISTENZA AL GELO FROST RESISTANCE RESISTANCE AU GEL FROSTBESTÄNDIGKEIT		RESISTE RESISTANT RÉSISTE BESTÄNDIG	RESISTE RESISTANT RÉSISTE BESTÄNDIG
	ISO 10545/6	RESISTENZA ALL'ABRASIONE PROFONDA DEEP ABRASION RESISTANCE RÉSISTENCE A L'ABRASION PROFONDE TIEFENVERSCHLEISSBESTÄNDIGKEIT	< 175 mm <sup>3</sup>	128 mm <sup>3</sup>	
	BOT 3000 WET DCOF	RESISTENZA ALLO SCIOLAMENTO SLIP RESISTANCE RESISTANCE AU GLISSEMENT BESTIMMUNG DER RUTSCHEMME EIGENSCHAFT	≥ 0,42	Tile 1 : 0.57 Tile 2 : 0.61 Tile 3 : 0.58	
	DIN 51130 R	WATER, OIL, GREASE, ETC. CREATE SLIPPERY CONDITIONS. FLOOR APPLICATIONS WITH EXPOSURE TO THESE CONDITIONS REQUIRE EXTRA CAUTION IN PRODUCT SELECTION.		R9	